





VIACRETE system data sheet

VIACRETE *MF standard SR^{VM}*

HACCP International certified, high grade slip resistance, seamless, antimicrobial, odourless, solvent free polyurethane concrete flooring system with excellent chemical resistance and textured matt finish.

SYSTEM BUILD-UP

-  Seal coat coloured:
VIACRETE PU-TC^{VM}
-  Wear coat coloured:
VIACRETE PU-MF^{VM} + scatter different aggregate
-  Primer for cementitious substrates:
VIACRETE PU-MF^{VM}
-  Substrate:
Concrete, cementitious screed and others

SYSTEM THICKNESS

4.0 – 6.0 mm



SYSTEM HIGHLIGHTS

- HACCP International certified
- Incorporates antimicrobial additive which inhibits the growth of bacteria, fungi, moulds and mildew
- Low emission tested according AgBB guidelines and other European standards as M1 classification
- Slip resistant surfaces R10-R13

APPLICATION FIELDS

- Wet processing zones
- Dairy production
- Fisheries and seafood processing
- Poultry and meat processing
- Commercial kitchen
- Foodstuff preparation
- Beverage production



SYSTEM BENEFITS

- Wide range of slip resistance R10-R13
- Odourless, non-tainting to food
- HACCP International certified and complies to GMP requirements
- Seamless finish
- Easy to clean and low maintenance (hot water cleanable)
- Fast return to service
- Available in many colours
- High impact resistance
- High abrasion resistance
- Chemical resistance
- Fire resistance class B_{fl-s1}

Manufacturer:

VIACOR Asia Sdn Bhd., No. 5 Jalan Sungai Terap 32/182, Bukit Rimau Industrial Park, 40460 Shah Alam, Selangor Darul Ehsan, Malaysia, tel: +603 5131 7777, fax: +603 5131 7878, email: sales@viacorasia.com, www.viacorasia.com

VIACRETE system data sheet




VIACRETE *MF standard SR^{VM}*

SUBSTRATE REQUIREMENT

Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength $\geq 1.5 \text{ N/mm}^2$, residual moisture content $< 4 \%$ -CM, with higher residual moisture and on substrates with moisture from the slab special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with VIASOL quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.

Detailed application instructions are available upon request or refer to the technical product data sheet.

TECHNICAL DATA

	property	Standard	result
	Compressive strength	EN 196 / ASTM C109	$\geq 45 \text{ N/mm}^2$
	Adhesive strength	EN ISO 4624	$>1.5 \text{ N/mm}^2$
	Shore-Hardness	EN ISO 868	D 75 after 28 d
	Heat resistance		-15°C to $+90^\circ\text{C}$
	Impact strength	EN 13813	$\geq 4 \text{ Nm}$ (IR4)
	Anti-microbial	Japanese Industrial Standard JIS Z 2801:2000	After 60 wash cycles 99.9% microbial growth reduction
	Flexural strength	ASTM C 348	$>20 \text{ N/mm}^2$
	Tensile strength	EN 196 / ASTM C109	$>10 \text{ N/mm}^2$
	Slip Resistance QS 0.4-0.8mm QS 0.7-1.2mm	TRRL pendulum slip test	Dry > 100 , wet > 25 Dry > 100 , wet < 41
	Slip Resistance QS 0.4-0.8mm QS 0.7-1.2mm	DIN 51130	R10, R11-V4 R12-V4, R12-V6
	Fire Resistance	EN13501-1	B _{f1} -s1

Remark: For further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore no liability claims can be derived from the system data sheet. As all VIACOR data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.viacor.asia or contact us directly)– all technical information is subject to change without prior notice
VIACOR products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

Manufacturer:

VIACOR Asia Sdn Bhd., No. 5 Jalan Sungai Terap 32/182, Bukit Rimau Industrial Park, 40460 Shah Alam, Selangor Darul Ehsan, Malaysia, tel: +603 5131 7777, fax: +603 5131 7878, email: sales@viacorasia.com, www.viacorasia.com